

Purolite™ Shallow Shell™ SSTC6000E

Poliestireno Gel, Resina Catiónica
Fuertemente ácida, Forma de sodio,
Tecnología Shallow Shell™*

PRINCIPALES APLICACIONES

- Ablandamiento - Industrial
- Ablandamiento - agua Potable
- Procesamiento de alimentos y bebidas
- Desmineralización cuando regenerado con ácidos

VENTAJAS

- SST shorter diffusion path benefits:
- Very low leakage
- Highly resistant to iron fouling
- Lower rinse volumes
- Lower operating costs
- Excellent physical/chemical stability

SISTEMAS

- Sistema Cocorriente de regeneración
- Tratamiento de agua potable

APROBACIONES REGULADORAS

- Certificado por la WQA, estándar NSF ANSI 61

ENVASE TÍPICO

- Bolsa de 1 pie³
- Bolsa de 25 L
- Tambor (fibra) de 5 pie³
- Supersack de 1 m³
- Supersack de 42 pie³

* SST® es una marca registrada de Purolite Corporation.

CARACTERÍSTICAS FÍSICAS Y QUÍMICAS:

Estructura del polímero	Gel reticulado poliestireno con divinilbenceno
Aspecto	Esferas
Grupo funcional	ácido sulfónico
Forma iónica	Na ⁺
Capacidad de peso seco (min.)	3.8 EQ/kg (Na ⁺ forma)
Retención de la humedad	40 - 48 % (Na ⁺ forma)
Rango de tamaño de esferas	500 - 1000 µm
< 300 µm (max.)	1 %
Coefficiente de uniformidad (max.)	1.3
Hinchamiento reversible, Na ⁺ → H ⁺ (max.)	8 %
Densidad específica	1.2
Peso de envío (aprox.)	775 - 825 g/L (48.4 - 51.6 lb/pie ³)
Límite de temperatura	100 °C (212.0 °F)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.