

Purolite Praesto™

Jetted SP200

Agarose Alto crosslink
Intercambiador de cationes fuertes,
200 µm particle size

PRINCIPALES APLICACIONES

- Lactoferrin Purification

APROBACIONES REGULADORAS

- Manufactured under GMP conditions

VENTAJAS

- Capacidades de enlace dinámico excelente para alta productividad y escalabilidad
- Rendimiento de flujo de presión excelente
- Selectividad alta resolución
- Excelente estabilidad química y física
- Soporte regulatório, Fuente segura, fsuplidor validado

CARACTERÍSTICAS FÍSICAS Y QUÍMICAS:

Estructura del polímero	Highly cross linked agarose
Aspecto	Spherical beads
Grupo funcional	Sulfopropyl
Estabilidad química	All commonly used aqueous buffers. 1M NaOH, 8M urea, 6M guanidine hydrochloride, 30% isopropanol and 70% ethanol
Evitar	Oxidising agents, cationic detergents
Capacidad iónica - mediana	0.10 - 0.16 mmol/ml H ⁺
Particle Size Distribution	100 - 300 µm
estabilidad de pH, CIP (corto plazo)	3 - 14
estabilidad de pH, rango de trabajo	4 - 13
Almacenaje recomendado	4 - 30 °C
Almacenaje recomendado	20% ethanol
Almacenaje recomendado	0.2M sodium acetate
Microbial Contamination; Colony Forming Units / ml suspension	≤ 20
Back Pressure at 500 cm/h; bar	<1

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puoliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puoliteresins.com or complete a Contact Us form via PuoliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.